



TRIBÙ

# TECHNICAL SPECIFICATIONS

Our 2025 fabric collection introduces a curated selection of solution-dyed acrylics. Soft to the touch yet engineered to offer superior UV resistance, these new fabrics confidently withstand fading and degradation. Please explore their technical specs, including performance levels in colour fastness, abrasion and pilling resistance.

# FABRIC PROPERTIES

## SUNBRELLA

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Natté White	01	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	3-4	5
Oyster	03	Cat. D	Sunbrella® Solution dyed acrylic	280	20.000	5	4-5
Natté Sandstone	04	Cat. D	Sunbrella® Solution dyed acrylic	290	>40.000	3-4	4-5
Natté Poivre	05	Cat. D	Sunbrella® Solution dyed acrylic	290	>40.000	3-4	4-5
Natté Dune	06	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	3-4	5
Papyrus*	07	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	340	25.000	3-4	5
Natté Carbon Sky	08	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4	5
Blush	11	Cat. D	Sunbrella® Solution dyed acrylic	260	25.000	4	5
Indian Summer	13	Cat. D	Solution dyed acrylic	275	12.000	4	3
Ashe*	15	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	340	25.000	4-5	5
Moss*	29	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	365	>40.000	4	4-5
Copper*	31	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	335	>40.000	4-5	4-5
Mahogany*	32	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	335	>40.000	4-5	4-5
Natté Frost Chiné	34	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Natté Olive	40	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4	5
Leaf*	42	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	340	25.000	4-5	5
Natté Anis	44	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Natté Mist	45	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Natté Stardust	46	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4	5
Natté Ochre	47	Cat. D	Sunbrella® solution dyed acrylic	290	25.000	4-5	5
Natté Nature Grey	64	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Natté Basalt	65	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Natté Silvergrey	69	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	3-4	5
Natté Charcoal	75	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5
Granite*	76	Cat. D	Sunbrella® 50% recycled acrylic - 47% arcylic - 3% PE	340	25.000	4-5	5
Natté Wengé	89	Cat. D	Sunbrella® Solution dyed acrylic	290	25.000	4-5	5

# FABRIC PROPERTIES

## LINEN

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Venice	E79	Cat. E	Solution dyed acrylic	592	15.000	4	4
Sandstone	E80	Cat. E	Solution dyed acrylic	530	15.000	4	4
Linen	E81	Cat. E	Solution dyed acrylic	530	20.000	3	4
White sand	E82	Cat. E	Solution dyed acrylic	530	20.000	3	4
Washed linen	E83	Cat. E	Solution dyed acrylic	530	20.000	3	4
Chalk	E84	Cat. E	Solution dyed acrylic	530	20.000	3	4
Granite	E85	Cat. E	Solution dyed acrylic	540	20.000	3	4
Oxford Blue	E86	Cat. E	Solution dyed acrylic	592	20.000	3	4
Burgundy	E100	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Sunset	E101	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Ruby	E102	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Mushroom	E103	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Dusty Rose	E104	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
White Quartz	E105	Cat. E	Solution dyed acrylic	530	40.000	3	4-5
Dark Blue	E107	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Frost Blue	E108	Cat. E	Solution dyed acrylic	540	40.000	3	4-5
Moss	E109	Cat. E	Solution dyed acrylic	592	40.000	3	4-5
Verdant Grey	E111	Cat. E	Solution dyed acrylic	592	40.000	3	4-5

# FABRIC PROPERTIES

**BASC**

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Seasalt	E51	Cat. E	Solution dyed acrylic	501	20.000	4	4
Flax	E54	Cat. E	Solution dyed acrylic	501	20.000	4	4
Alabaster	E55	Cat. E	Solution dyed acrylic	501	20.000	4	4
Mellow Ochre	E56	Cat. E	Solution dyed acrylic	501	20.000	4	4
Papyrus	E57	Cat. E	Solution dyed acrylic	501	20.000	4	4
Artic	E91	Cat. E	Solution dyed acrylic	501	20.000	4	4
Mushroom	E93	Cat. E	Solution dyed acrylic	501	20.000	4	4

# FABRIC PROPERTIES

## YUTTU

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Seasalt	E61	Cat. E	Solution dyed acrylic	501	20.000	4	4
Flax	E64	Cat. E	Solution dyed acrylic	501	20.000	4	4
Alabaster	E65	Cat. E	Solution dyed acrylic	501	20.000	4	4
Mellow Ochre	E66	Cat. E	Solution dyed acrylic	501	20.000	4	4
Papyrus	E67	Cat. E	Solution dyed acrylic	501	20.000	4	4
Artic	E95	Cat. E	Solution dyed acrylic	501	20.000	4	4
Mushroom	E97	Cat. E	Solution dyed acrylic	501	20.000	4	4

# FABRIC PROPERTIES

## DUAS

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Cotton White	E120	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Cream White	E121	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Almond	E122	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Linen	E123	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Carbon Sky	E124	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Wengé	E125	Cat. E	Solution dyed acrylic	640	30.000	3-4	4
Ivory	E130	Cat. E	Solution dyed acrylic	480	20.000	3-4	4
Dunes	E131	Cat. E	Solution dyed acrylic	480	20.000	3-4	4
Rustic Brown	E132	Cat. E	Solution dyed acrylic	480	20.000	3-4	4

# FABRIC PROPERTIES

## KNIT

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Morning Dew	E32	Cat. E	100% solution dyed polyolefin	710	40.000	3-4	4.5
Silverstone	E34	Cat. E	100% solution dyed polyolefin	710	40.000	3-4	4.5
Dunes	E35	Cat. E	100% solution dyed polyolefin	995	40.000	3	4-5
Wengé	E39	Cat. E	100% solution dyed polyolefin	710	40.000	3-4	4.5
Rosemary	E43	Cat. E	100% solution dyed polyolefin	710	40.000	3-4	4.5
Licorice	E44	Cat. E	100% solution dyed polyolefin	710	40.000	3	4.5
Mellow Ochre	E45	Cat. E	100% solution dyed polyolefin	710	40.000	3	4.5
Dark Copper	E48	Cat. E	100% solution dyed polyolefin	710	40.000	2	4.5

# FABRIC PROPERTIES

## NATURAL

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Seashell	B154	Cat. E	Solution dyed acrylic	365	25.000	4	4
Cloudy Sky	B155	Cat. E	Solution dyed acrylic	365	25.000	4-5	4
Aged Ivory	B156	Cat. E	Solution dyed acrylic	365	25.000	4	4
Umbra	B157	Cat. E	Solution dyed acrylic	365	25.000	4-5	4
Off-White	B193	Cat. E	Solution dyed acrylic	365	25.000	5	4
Dark Brown	B194	Cat. E	Solution dyed acrylic	365	25.000	5	4

# FABRIC PROPERTIES

## NESSO

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Almond	E70	Cat. E	Solution dyed acrylic	450	12.000	3	4-5
Ochre Mist	E71	Cat. E	Solution dyed acrylic	450	12.000	3	4-5
Carbon Sky	E72	Cat. E	Solution dyed acrylic	450	15.000	3	4-5
Sky Mist	E73	Cat. E	Solution dyed acrylic	450	15.000	3	4-5
Ice Blue	E74	Cat. E	Solution dyed acrylic	450	15.000	3	4-5
Leaf	E75	Cat. E	Solution dyed acrylic	450	15.000	3	4-5
Sunset	E76	Cat. E	Solution dyed acrylic	450	15.000	3	4-5

# FABRIC PROPERTIES

RUSTIC WEAVE	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
	Dark Grey	B140	Cat. E	Solution dyed acrylic	400	12.000	4
Oyster	B143	Cat. E	Solution dyed acrylic	400	12.000	4	3-4
Cord	B144	Cat. E	Solution dyed acrylic	470	21.000	4	3-4
Ice Grey	B146	Cat. E	Solution dyed acrylic	470	21.000	4	3-4
Black	B147	Cat. E	Solution dyed acrylic	400	12.000	4-5	3-4
Abricot	B150	Cat. E	Solution dyed acrylic	400	12.000	3-4	3-4
Brown	B151	Cat. E	Solution dyed acrylic	400	12.000	4-5	3-4
Fresco	B152	Cat. E	Solution dyed acrylic	400	12.000	3-4	3-4
Lagoon	B153	Cat. E	Solution dyed acrylic	400	12.000	4	3-4

# FABRIC PROPERTIES

## NARAM

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Pearl	F19	Cat. F	Solution dyed acrylic	1.360	25.000	4-5	4
Almond	F20	Cat. F	Solution dyed acrylic	1.360	25.000	4-5	4
Warm Cotton	F21	Cat. F	Solution dyed acrylic	1.360	25.000	4-5	4
Oyster	F80	Cat. F	Solution dyed acrylic	971	30.000	3	4
Herb	F81	Cat. F	Solution dyed acrylic	971	30.000	3	4
Rosemary	F82	Cat. F	Solution dyed acrylic	971	30.000	3	4
Frost	F84	Cat. F	Solution dyed acrylic	971	30.000	3	4
Denim	F85	Cat. F	Solution dyed acrylic	971	30.000	3	4
Indigo	F86	Cat. F	Solution dyed acrylic	971	30.000	3	4
Moss	F87	Cat. F	Solution dyed acrylic	971	30.000	3	4
Verdant	F88	Cat. F	Solution dyed acrylic	971	30.000	3	4
Ochre	F89	Cat. F	Solution dyed acrylic	971	30.000	3	4
Copper	F90	Cat. F	Solution dyed acrylic	971	30.000	3	4
Merlot	F91	Cat. F	Solution dyed acrylic	971	30.000	3	4
Cerise	F92	Cat. F	Solution dyed acrylic	971	30.000	3	4

TRIBÙ

# FABRIC PROPERTIES

SIVA

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Cotton White	F50	Cat. F	Solution dyed acrylic	700	25.000	3-4	4

TRIBÙ

# FABRIC PROPERTIES

SUJÀN

	Code	Category	Composition	Weight (g/m <sup>2</sup> )	Abrasion Resistance Martindale	Colour fastness to UV scale of 1-5	Pilling scale of 1-5
Hemp	F01	Cat. F	Solution dyed acrylic	1.000	5.000	4	3-4
Moss	F02	Cat. F	Solution dyed acrylic	1.000	5.000	4	3-4
Ochre	F04	Cat. F	Solution dyed acrylic	1.000	5.000	4	3-4
Nature Grey	F17	Cat. F	Solution dyed acrylic	971	5.000	4	3-4

